检测到当前网页不是中文网页，是否要翻译成中文? 翻译 不翻译 不再提示

Property	Unit	Test Method	Test Condition	General Purpose
Model				AC2300
Melt Flow Index	g/10 min	ASTM D-1238	240℃ × 5kg	7
Melt Flow Index	g/10 min	ASTM D-1238	260℃ × 5kg	17
IZOD Impact Strength	kg-cm/cm	ASTM D-256	23 ℃	60
Specific Gravity	g/cm3	ASTM D-792	23 ℃	1.14
Tensile Strength	kg/cm^2	ASTM D-638	23 ℃	560
Flexural Strength	kg/cm^2	ASTM D-790	23 ℃	920
Flexural Modulus	kg/cm^2	ASTM D-790	23 ℃	23000
Rockwell Hardness	R-scale	ASTM D-785	23 ℃	R-116
Heat Deflection Temperature	℃	ASTM D-648	Unannealed 6.4mm, 1.8 MPa	112
Molding Shrinkage	%	ASTM D-955	Flow dir.料流方向	0.4 ~ 0.6
Flammability	-	UL-94	FILE NO. E162823	1.5mm HB
Features	Metal plating			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.
TEL:+886-2-27122211 FAX: +886-2-27131649
Address: Building A2, No. 380, Section 6, Nanjing East Road, Neihu District, Taipei City 11470
www.fcfc-plastics.com