Bai du 翻译 检测到当前网页不是中文网页，是否要翻译成中文? 翻译 不翻译 不再提示

PC/ABS Alloy

Property	Unit	Test Method	Test Condition	Self Extinguishing Grade
Model				AC3100
Melt Flow Index	g/10 min	ASTM D-1238	240℃ × 5kg	25
Melt Flow Index	g/10 min	ASTM D-1238	260℃ × 2.16kg	17
IZOD Impact Strength	kg-cm/cm	ASTM D-256	23℃, 3.2mm, Notched	65
Specific Gravity	-	ASTM D-792	23℃/23℃	1.18
Tensile Strength	kg/cm^2	ASTM D-638	23 ℃	650
Flexural Strength	kg/cm^2	ASTM D-790	23 ℃	1000
Flexural Modulus	kg/cm^2	ASTM D-790	23 ℃	25000
Rockwell Hardness	R-scale	ASTM D-785	23 ℃	R-118
Vicat Softening Point	℃	ASTM D-1525	VICAT(10N ℃)	107
Heat Deflection Temperature	℃	ASTM D-648	Unannealed 18.6 kg/cm^2 (1.8Mpa)(6.4mm)	90
Molding Shrinkage	%	ASTM D-955	3.2mm	0.4 ~ 0.6
Combustibility		UL-94	File No. E162823	v-0 1 ~ 3 mm 5VA 3 mm 5VB 2.3 mm
Features	Flame retardant, Halogen free			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.
TEL:+886-2-27122211 FAX: +886-2-27131649
Address: Building A2, No. 380, Section 6, Nanjing East Road, Neihu District, Taipei City 11470
www.fcfc-plastics.com